

# CERAN WR 2



Grease



**Extreme pressure water resistant high temperature calcium sulfonate complex grease.**

## APPLICATIONS

**Multi purpose heavy duty water resistant grease. Industrial applications**

**Recommendation**

- **CERAN WR 2** is a multi purpose extreme pressure grease, formulated for the lubrication of all kinds of industrial, marine and off shore applications, operating under the most severe conditions. (water, heat, dust and other pollution).
- **CERAN WR 2** is also suitable as EP multi purpose grease, in "off road" applications where water is in frequent contact with the grease.
- Always avoid contamination of the grease by dust and/or dirt when applying. Preferably use a pneumatic pump system or cartridges.

## SPECIFICATIONS

- Performances meet all Voith VN 108 requirements (soap is not lithium but calcium sulfonate complex).
- ISO 6743-9: L-XBFB 2
- DIN 51 502: KP2R -25
- Marine standard STM 310A (NATO G 460)

## ADVANTAGES

**True multi purpose  
High loads  
Water resistant  
High temperatures  
Anti corrosion  
No harmful substances**

- Thanks to its very sophisticated formula and performance reserves, **CERAN WR 2** meets the most stringent industrial requirements. Its range of applications is extensive, as a result it can replace and outclass numerous conventional greases.
- Excellent thermal stability. It regains its original texture after cooling to ambient temperature.
- Remarkable load resistance thanks to its naturally high extreme pressure and anti-wear properties.
- Extraordinary water resistance, no significant loss of consistency is observed even with high amounts of water entering the grease.
- Excellent anti-oxidation and anti-corrosion properties thanks to the very nature of the calcium sulfonates, also in the presence of sea water.
- **CERAN WR 2** does not contain lead, or other heavy metals considered harmful to human health and the environment.

TYPICAL CHARACTERISTICS	METHODS	UNITS	CERAN WR 2
Soap/thickener		-	Calcium Sulfonate
NLGI grade	ASTM D 217/DIN 51 818	-	2
Color	Visual	-	Brown
Appearance	Visual	-	Smooth
Operating temperature range		°C	- 25 to 180
Penetration at 25°C	ASTM D 217/DIN 51 818	0.1 mm	265-295
Four ball weld load	ASTM D 2596	kgf	500
Anti-rust performance SKF- EMCOR	DIN 51 802/IP220/NFT 60-135/ISO 11007	rating	0-0
Dropping point	IP 396/NFT 60 102 C	°C	> 300
Kinematic viscosity of the base oil at 40°C	ASTM D 445/DIN 51 562-1/ISO 3104/ IP71	mm <sup>2</sup> /s (cSt)	180

Above characteristics are mean values given as an information.

**TOTAL LUBRIFIANTS**  
**Industrie & Spécialités**  
29-04-2009 (supersedes 27-04-2009)  
CERAN WR 2  
1/1



This lubricant used as recommended and for the application for which it has been designed does not present any particular risk.  
A material safety data sheet conforming to the regulations in use in the E.C. is obtainable via your commercial adviser [www.quick-fds.com](http://www.quick-fds.com).